

Resin Cartridge

(For Rock Bolt)

WISE-E 16 mainly composed by polyester and hardener sealed inside the PE plastic foil pack. The cartridge is widely applied as fixation material for bolting or anchoring in the field of mining, tunneling or other foundation works.

Special features:

- ☀ The very durable P.E. film foil pack is preventing broken during push in.
- ☀ Polyester Resin bonded entirely with borehole to gain anchoring strength
- ☀ Compressive strength up to 80 N/mm² (ASTM D695-89)
- ☀ Bolt pull loading test (up to 15 tonf) available 30 - 60 minutes after application
- ☀ The gelling time is adjustable according to the different requirements.



TECHNICAL DATA

Diameter	Length	Volume	Bolt OD	Borehole	Bondage L
40 mm OD	500mm	625c.c	40mm	50mm	770mm
			32mm	44mm	730mm
40 mm OD	345mm	430c.c	40mm	50mm	530mm
			32mm	44mm	500mm
			25mm	40mm	460mm
30 mm OD	500mm	340c.c	32mm	40mm	830mm
			25mm	35mm	680mm
			20mm	32mm	630mm
30 mm OD	330mm	225c.c	32mm	38mm	790mm
			25mm	32mm	660mm
			20mm	28mm	480mm
25 mm OD	330mm	155c.c	25mm	35mm	230mm
			20mm	30mm	290mm
			16mm	28mm	270mm

Remarks: Special dimension is available upon request.

Borehole diameter is recommended to be 7~12mm bigger than rock bolt.

For very fractured geology the bonding length will relatively reduce 25~50%.

REACTION TIME

Reacting time of **WISE-E16** would be affected by surrounding temperature, generally 10°C up the gelling time becomes roughly half time shorten.

Curing time means the resin mixture becoming harden after the gelling time, for **WISE-E16** the hardening time is around 15 min. after gelling.


Gelling time (GREEN-Standard)

Gel time in 10 - 15 min. (25°C) **GREEN** Cartridge is available when ordering.


(RED-Fast Type)

Gel time in 3 - 5 min. (25°C) **RED** Cartridge is available when ordering.


INSTALLATION SEQUENCE FOR BOLTING




Borehole drilling & Flush cleaning



Insert the WISE-E16 As designed quantity



Spin WISE-E16 As special adapter (Full-threaded Dowel)



Bolt-Spider Fixing bolt upwards Spin & Mix resin



Storage 180 days quality is assured under 35°C without sun exposure.

Well Protected Packing 40 cartridges are loaded per carton for delivery